

# Hot Stamp

## SUPPLY COMPANY

### TECHNICAL DATA SHEET

**Series: GB01, BFD, BKR, BFR, CA26, CB26**

**Substrate**

ABS  
Acetate  
Acrylic  
Lacquered Wood  
Polycarbonate  
Coated Paper

Polystyrene  
Polyurethane  
Rigid PVC  
Satin Ribbon  
Polyester

**Die Temperature Range**

220-300° F Metal  
104-149° C Metal  
250-425° Silicone  
121-218° Silicone

**Carrier**

16 Micron (60ga.)  
Polyester Film

**Series: BD68, MK68, SA68**

**Substrate**

ABS (BD Formulation)  
Acetate (BD Formulation)  
PE (MK Formulation)  
Lacq. Wood (BD Formulation)  
Coated Paper (BD Formulation)

PVC (BD Formulation)  
Acrylic (BD Formulation)  
PP (SA Formulation)  
Polystyrene (BD)  
UV Coated Paper (SA)

**Die Temperature Range**

220-300° F Metal  
104-149° C Metal  
250-425° F Silicone  
121-218° C Silicone

**Carrier**

16 Micron (60ga.)  
Polyester Film

**Series: LFQ**

**Substrate**

Acetate Laminated Stock  
Book Stock  
Kromekote  
Dry Paper Stock  
Inked/Lacquered Stock  
Lacquered Wood  
Labeled Stock (Self-Ad)

Leather (Coated)  
Leather (Uncoated)  
Pyroxylin  
Satin Ribbon  
Velour Paper Stock  
UV Coated

**Die Temperature Range**

250-350° F Metal  
120-180° C Metal

**Carrier**

16 Micron (60ga.)  
Polyester Film